



455 Bryant St., North Tonawanda, NY 14120
 Phone: (716) 694-4000 Fax: (716) 694-1450
 E-Mail: sales@taberindustries.com
 www.TaberIndustries.com

Test Data:

Sample	Wt. Initial (g)	Wt. Final (g)	Δ Wt. (g)
ST II A	195.6253	195.6250	0.0003
B	200.3072	200.3069	0.0003
C	196.8444	196.8442	0.0002
		AVERAGE	0.0003
		St. Dev.	0.0001

Samples are being returned for examination. Should you have any questions about these results, please contact me at the information below.

Cliff Fee

Sales Application Engineer
 Fee C@TaberIndustries.com
 Taber Industries
 455 Bryant St.
 North Tonawanda, NY 14120 USA
 Phone (716)694-4000 Ext.118 or Toll Free (800)333-5300

Data from referenced report:

Sample	Wt. Initial (g)	Wt. Final (g)	Δ Wt. (g)
SS IV A	212.7693	212.7653	0.0040
B	207.1683	207.1602	0.0081
C	214.7304	214.7249	0.0055
		Average	0.0059
		St.Dev.	0.0021
Sanitech Gloss A	212.5898	212.5882	0.0016
B	217.2432	217.2411	0.0021
C	208.2569	208.2548	0.0021
		Average	0.0019
		St.Dev.	0.0003
NS-01 A	203.3329	203.3323	0.0006
B	206.4796	206.4787	0.0009
C	205.6939	205.6927	0.0012
		Average	0.0009
		St.Dev.	0.0003
Sanimax A	218.6034	218.6021	0.0013
B	208.8883	208.8865	0.0018
C	210.6932	210.6903	0.0029
		Average	0.0020
		St.Dev.	0.0008

Providing solutions to help our customers make better measurements



455 Bryant St., North Tonawanda, NY 14120
Phone: (716) 694-4000 Fax: (716) 694-1450
E-Mail: sales@taberindustries.com
www.TaberIndustries.com

SS V	209.6206	209.6193	0.0013	
	205.8190	205.8152	0.0038	
	205.6408	205.6394	0.0014	
		Average	0.0022	
		St.Dev.	0.0014	
AD-01 A	204.0563	204.0554	0.0009	
	B	203.4344	203.4331	0.0013
	C	209.8106	209.8089	0.0017
		Average	0.0013	
		St.Dev.	0.0004	

Providing solutions to help our customers make better measurements

Transducer • Materials Test & Measurement • Kenco Press